

# AMS Seal WP™

Anionic Medium Setting Patching Emulsion  
Winter Patch



[www.michiganpaving.com](http://www.michiganpaving.com)

## PRODUCT DESCRIPTION

**AMS Seal WP™** is a high performance, medium set asphalt emulsion designed for spray patch repairs of asphalt and concrete pavements in cool or cold months or climatic conditions. It is designed for and ideally used in DuraPatch machines or similar units.

**AMS Seal WP™** is designed to exceed agency specifications and to provide effective patching, large crack sealing, and failing pavement joint binders. This emulsion is simple to handle and provides long shelf life.

**AMS Seal WP™** Can be used for the maintenance of roads and other asphalt pavements such as pothole patching and other spray seal patch operations. It is also suitable for minor chip seal or bar seal applications.

**Mix Design:** Use full strength. For a typical spray patch application, material can be sprayed in alternating layers of binder and aggregate to produce a uniform sealed surface, with cover aggregate as last layer.

### Features/Benefits

- Economical
- Stability and long shelf life
- Good pretreatment for chip seal or other surface treatments
- Compatibility with a variety of aggregates
- Versatility

**Availability:** Bulk available at terminal or tanker load delivery; typically, from November through March. Totes available by request.

### Application

Optimum application of **AMS Seal SP™** occurs when the pavement temperature is 50°F and rising\*. It can be applied in high humidity but this will prolong the break time. Vehicular traffic should be kept off of the treatment until the emulsion is cured. The area to be treated should be free of standing water, debris, and oils. Aggregate should be clean and free of fines or dust for the best adhesion results and performance of patching equipment. If the emulsion freezes during use; typically indicated by a chalky broken appearance, and before adhesion to aggregate, discontinue use.

\*Cure time can vary with environmental conditions.



### Spray Patch Emulsion Handling Guidelines

- Apply at 150°F to 160°F
- At the end of each day's use empty unit of emulsion/asphalt.
- Using small amounts of diesel flush applicator piping and lines at the end of each day's use.
- To heat emulsion gently use non-direct contact heating methods
- Direct contact heat should only be done when absolutely necessary. This should be done sporadically and with recirculation or agitation if possible. Note: Emulsion which directly contacts any heat source above 210°F will experience break and separation.
- Emulsion separation will occur if frozen or boiled.

### MAINTENANCE

Tools and equipment may be cleaned with a suitable asphalt cleaner.

### SPECIFICATIONS – TECHNICAL DATA

#### AMS Seal SP™

<u>Emulsion Tests</u>	<u>Specification</u>	<u>Typical Results</u>
Viscosity, 50°C, SFS	75 – 400	130
Residue by Distillation, %, min	62	65.0 +/- 3.0
Demulsibility, %, min	40	45 +
Penetration, dmm	100 - 200	125 - 150

**AWARD WINNING ASPHALT PAVING & SUPPLY SINCE 1959**

Michigan Paving & Materials Co.

1950 Williams St.  
Alma, MI 48801

Tel: 989-402-5932



Michigan Paving & Materials Co.

3125 E Front Street  
Monroe, MI 48161

Tel: 734-241-9189